

DMR Material PPC-ND69

High Density Polyethylene Engineering Thermoplastic



MATERIAL DATA SHEET (Version 5.0 – 05.2019)

Description

PPC-ND69 is an amorphous polypropylene co-polymer which provides high heat resistance, strength, toughness and chemical corrosion resistance. PPC is particularly suitable for use in the chemical engineering industry and clean room environments due to its food safe properties.

Physical Properties

Property	Test method	Unit	Typical value
Colour			Natural / White
Shore Hardness	Shore D	DIN ISO 868	69
Yield stress	ISO 527	MPa	23
Elongation at break	ISO 527	%	>50
Tensile Modulus of elasticity	ISO 527	MPa	1100
Water absorption	ISO 62	%	<0.1
Density	ISO 1183-1	g/cm ³	0.91
Surface resistivity	IEC 60093	Ohm	>10 ¹³
Volume resistivity	IEC 60093	Ohm cm	>10 ¹⁴
Melting Point	ISO 11357-3	°C	162-167
Heat Deflection Temperature	ISO 306 B	°C	85
Coefficient Of Linear Thermal Expansion	DIN 53752	10 ⁻⁶ K ⁻¹	120-190
Service temperature (Long term)		°C	-30 to +100
Service temperature (short term - max)		°C	+150

Main Characteristics

- FDA compliant
- Good chemical resistance
- Good heat resistance
- Low water absorption
- Tough material

Typical products

- Anti-Extrusion / Back-up Rings
- Bearing rings / guide rings
- Bushes
- Bespoke parts
- Liners

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales@dmrseals.co.uk . Web: www.dmrseals.co.uk

DMR Seals Ltd believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however DMR Seals Ltd makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.