

DMR Material PTCBM-BLD56

Green Special Mineral Reinforced PTFE




MATERIAL DATA SHEET (Version 5.1 – 05.2019)



High Temperature



Chemical Resistance



Low Friction

Description

DMR PTCBM-BLD56 is a special mineral reinforced and pigmented PTFE that helps provide increased durability when compared to standard virgin PTFE through its increased wear, and pressure resistance.

PTCBM-BLD56 is recommended for sealing components in light duty, dynamic reciprocating, rotating and oscillating applications requiring a PTFE material with improved properties over standard virgin PTFE.

Physical Properties

Property	Test method	Unit	Typical value
Colour			Turquoise
Hardness	ASTM D2240	Shore D	≥51
Tensile strength (23°C)	ISO 527	N/mm ²	≥24
Elongation at break (23°C)	ISO 527	%	≥250
Tensile modulus	DIN 53457	N/mm ²	1200
Density	ASTM D792	g/cm ³	2.14-2.18
Coefficient of thermal expansion (25-100°C)	-	10 ⁻⁵ (mm/mm)/°C	12-13
Coefficient of friction	ASTM D41894	Points	0.06-0.08
Service temperature*		°C	-200/+260

* (Testing in application is mandatory)

Main Characteristics

- Increased wear resistance compared to virgin PTFE
- Extreme low friction properties
- Good replacement for virgin PTFE in dynamic duty
- Good in dry or poorly lubricated applications

Typical products

- Spring energised seals
- Packing set V rings
- Valve stem seals
- Rotary composite seals

Typical Applications

Due to its improved durability in comparison to standard virgin PTFE, PTCBM-BLD56 is commonly used as a sealing material in various low duty applications where its low friction properties are of the upmost importance.

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales@dmrseals.co.uk . Web: www.dmrseals.co.uk

DMR Seals Ltd believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however DMR Seals Ltd makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.