

DMR Material PTE25-CRD58

Polymer Reinforced PTFE




MATERIAL DATA SHEET (Version 5.1 – 05.2019)



High Temperature



Chemical Resistance



Low Friction



Wear Resistance

Description

PTE25-CRD58 is a filled proprietary polymer reinforced PTFE that has outstanding wear and temperature resistance and does not wear metallic surfaces, it is commonly referred to as Ekonol® filled PTFE. PTE25-CRD58 resists self-wear better than most other filled PTFE materials, it has good chemical resistance, combined with very low thermal expansion, making it a unique filled grade of PTFE.

PTE25-CRD58 is recommended for use with soft (un-hardened) metals and applications involving gases, high temperature and aggressive environments where it increased wear resistance is required. It should **not** be used in any applications where steam, concentrated Sulphuric acid and strong Alkalis are present.

Physical Properties

Property	Test method	Unit	Typical value
Colour			Beige
Density	ASTM D792	g/cm ³	1.80-2.0
Hardness	ASTM D2240	Shore D	>56
Tensile Strength	ISO 527	N/mm ²	>7
Elongation at break	ISO 527	%	>150
Service temperature *		°C	-200 to +260

Ekonol® is a registered trademark of SOHIO Co

Main Characteristics

- Good compressive strength
- Good sliding ability
- Excellent resistance to wear
- Lower creep rate compared to unfilled / Virgin PTFE
- Excellent high temperature resistance

Typical products

- Spring energised seals
- Wear strip
- Bearing rings / guide rings
- Bushes
- Valve seat seals

Typical Applications

PTE25-CRD58's unique anti wear properties and high temperature resistance make it an excellent material choice for rotary seals or high frequency dynamic applications working on soft / un-hardened metals in aggressive environments.

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales@dmrseals.co.uk . Web: www.dmrseals.co.uk

DMR Seals Ltd believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however DMR Seals Ltd makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.