

# DMR Material PTGVF-MD63

## Maroon Special Mineral Reinforced PTFE




### MATERIAL DATA SHEET (Version 5.1 – 05.2019)




High Temperature



Chemical Resistance



Low Friction



Wear Resistance

### Description

DMR PTGVF-MD63 is special mineral reinforced PTFE that provides increased durability through its excellent wear, temperature and pressure resistance.

PTGVF-MD63 is recommended for high wear components in dynamic reciprocating, rotating and oscillating applications requiring a PTFE material with low cold-flow ability.

### Physical Properties

Property	Test method	Unit	Typical value
Colour			Maroon
Hardness	DIN 53505	Shore D	62-64
Tensile Strength (23°C)	DIN 53455	N/mm <sup>2</sup>	16-20
Elongation at break (23°C)	DIN 53455	%	240-280
Tensile Modulus	DIN 53457	N/mm <sup>2</sup>	1200
Density	ISO 12086	g/cm <sup>3</sup>	2.22-2.26
Coefficient Of Thermal Expansion (20-150°C)	-	1/K.10 <sup>-5</sup>	9.4
Coefficient Of Thermal Expansion (150-260°C)	-	1/K.10 <sup>-5</sup>	12.8
Deformation after 24h @ 23°C 15 N/mm <sup>2</sup>	ASTM-D621	%	7.5
Wear K.10 <sup>-8</sup>	DIN 53481	cm <sup>3</sup> .min/kg.m.h	7.7

### Main Characteristics

- Excellent wear resistance
- Capable of high PV values
- Extreme low friction properties
- Does not abrade mating surfaces
- Excellent in dry or poorly lubricated applications
- FDA Compliant material

### Typical products

- Spring energised seals
- Wear rings
- Bearing rings / guide rings
- Packing set V rings
- Valve stem seals
- Rotary seals

### Typical Applications

Due to its excellent durability and low cold-flow ability PTGVF-MD63 is commonly used as a bearing and sealing material in various applications where resistance to pressure and wear are of the utmost importance.

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: [sales@dmrseals.co.uk](mailto:sales@dmrseals.co.uk) . Web: [www.dmrseals.co.uk](http://www.dmrseals.co.uk)

DMR Seals Ltd believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however DMR Seals Ltd makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.