

DMR Material PTV-WD57

Virgin PTFE Fluoropolymer Material



MATERIAL DATA SHEET (Version 5.0 – 05.2019)



High Temperature



Chemical resistance



FDA Compliant

Description

DMR Seals material PTV-WD57 is a standard unfilled/virgin PTFE compound (commonly referred to as Teflon™). PTV-WD57 has excellent chemical resistance and low friction properties making it an ideal choice for a wide range of sealing applications. Virgin PTFE presents high elastic deformation and poor rebound under load, so generally requires an energising element to help improve these properties, such as an O-Ring or metallic spring energiser.

Physical Properties

Property	Test method	Unit	Typical value
Colour			White
Density	ASTM D792	g/cm ³	2.15-2.18
Hardness	ASTM D2240	Shore D	≥51
Tensile strength	ISO 527	N/mm ²	≥24
Elongation at break	ISO 527	%	>250
Deformation under load *	ASTM D621	%	≤17
Permanent deformation**	ASTM D621	%	≤9
Coefficient of linear thermal expansion ***	ASTM D696	10 ⁵ (mm/mm)/ °C	12-13
Minimum service temperature ****		°C	-200
Maximum service temperature ****		°C	+260

* (24 Hours @ 23°C – 13.7N/mm²)

** (24 Hr relaxation @ 23°C)

*** (25 to 100°C)

**** (Testing in application is mandatory)

Teflon™ is a registered trademark of the Chemours company.

Main Characteristics

- Excellent chemical resistance
- Excellent low friction properties
- Excellent temperature range
- FDA compliant
- Wide range of uses

Typical products

- Soft seat seals
- Spring energised seals
- Gaskets
- Static Seals & O-Rings
- Back-Up Rings

Typical Applications

Due to its excellent low frictional properties, temperature and chemical resistance PTV-WD57 is a good choice for soft seat seals, spring energised seals and back-up rings commonly used in the sealing industry.

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales@dmrseals.co.uk . Web: www.dmrseals.co.uk

DMR Seals Ltd believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however DMR Seals Ltd makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.