

DMR Material PTX84-CRD60

Polymer Reinforced PTFE




MATERIAL DATA SHEET (Version 5.1 – 05.2019)




High Temperature



Chemical Resistance



Low Friction



Wear Resistance

Description

DMR PTX84-CRD60 is polymer reinforced PTFE that has outstanding wear and temperature resistance and does not wear hardware surfaces. It resists wear better than most other filled PTFE materials, it has excellent chemical resistance, low thermal expansion and some of the lowest friction properties of any PTFE, making it ideal for start/stop applications.

PTX84-CRD60 is recommended for use with soft (un-hardened) metals or plastics and applications involving gases or high temperature. It should **not** be used in any applications where steam, concentrated Sulphuric acid and strong Alkalis are present.

Physical Properties

Property	Test method	Unit	Typical value
Hardness	DIN 53505	Shore D	59-62
Tensile Strength (23°C)	DIN 53455	N/mm ²	23-27
Elongation at break (23°C)	DIN 53455	%	240-320
Tensile Modulus	DIN 53457	N/mm ²	820
Density	ISO 12086	g/cm ³	2.03-2.09
Ball Pressure Hardness	DIN53456	N/mm ²	62-68
Coefficient Of Thermal Expansion (20-100°C)	-	1/K.10 ⁻⁵	10
Coefficient Of Thermal Expansion (150-260°C)	-	1/K.10 ⁻⁵	13
Deformation after 24h @ 23°C	ASTM-D621	%	10
Wear K.10 ⁻⁸	DIN 53481	cm ³ .min/kg.m.h	6.5

Main Characteristics

- Excellent wear resistance
- Capable of high PV values
- Extreme low friction properties
- Does not abrade mating surfaces
- Excellent in dry or poorly lubricated applications

Typical products

- Spring energised seals
- Wear rings
- Bearing rings / guide rings
- Packing set V rings
- Valve stem seals

Typical Applications

Due to its excellent low friction values, wear resistance and low abrasion properties PTX84-CRD60 is commonly used as a sealing material for spring energised seals, Lipseals and packings in various applications .

Tel: 0044 (0) 114 243 2777 . Fax: 0044 (0) 114 242 2300 . Mail: sales@dmrseals.co.uk . Web: www.dmrseals.co.uk

DMR Seals Ltd believes that the information above is an accurate description of the typical characteristics and/or uses of the product or products, however DMR Seals Ltd makes no warranty, expressed or implied, that parts manufactured from this / and or any other material will perform satisfactorily in the customers application. It is the customers responsibility to thoroughly test products in their specific application to determine performance, efficiency and safety for each end-use product, device or application. The information and data contained herein are based on standard test pieces according to the corresponding ISO, DIN & ASTM standards and cannot be directly related to finished seals, gaskets or other sealing products and should be used only as a general guide.